



Laboratory Test Certificate

PORTLAND CEMENT - TYPE I/II

Source: Asia Cement-Hualein Plant, Taiwan

Chemical (C114)

Item (%)	Value	Limit
Silicon Dioxide (SiO ₂)	20.9	
Aluminum Oxide (Al ₂ O ₃)	3.95	6.0 Max
Ferric Oxide (Fe ₂ O ₃)	2.9	6.0 Max
Calcium Oxide (CaO)	63.6	
Magnesium Oxide (MgO)	3.4	6.0 Max
Sulfur Trioxide (SO ₃)	2.7	3.0 Max
Sodium Oxide (Na ₂ O)	0.19	
Potassium Oxide (K ₂ O)	0.53	
Loss on Ignition (LOI)	2.91	3.5 Max
Insoluble Residue	0.57	1.50 Max
Limestone %	4.5	5.0 Max
Potential phase composition (%)		
C ₃ S	61.7	
C ₂ S	13.3	
C ₃ A	5.5	8 Max
C ₄ AF	8.9	
Alkali Equivalent (NaEq)	0.54	

Physical Properties

Comp. Strength	Value	(Min.)
3 Days	4040 psi	1740 psi
	(27.8 MPa)	(12.0 MPa)
7 Days	5130 psi	2760 psi
	(35.3 MPa)	(19.0 MPa)
28 Days**	6690 psi	4060*psi
	(46.1 MPa)	(28.0*MPa)
Blaine Fineness:	4060 cm ² /gr	2600 Min.
Air Content:	7.4 %	12.0 %Max
Vicat C191 Init Set:	145 min.	45 Min
Vicat C191 Final Set:	275 min.	375 Max
Paste False Set:	84 %	50*% Min

* - optional requirements , Table 4.

** - 28 Days Compressive Strength from previous month.

We certify that the above described cement, at the time of shipment, meets the standard chemical and physical requirements of ASTM C150-22, Type I/II, low alkali (Table 1).

Cement Division

Office: 99-1300 Halawa Valley Street
 Aiea, HI 96701
 Phone (808) 532-3400

Daniel K. Paaaina III
 Chemist