HAWAIIAN CEMENT
A subsidiary of Knife River Corporation

Hawaiian Cement - Cement Division
99-1300 Halawa Valley Street
Aiea, Hawaii 96701
Phone: (808) 673-4200 Fax: (808) 441-7692
www.hawaiiancement.com

PORTLAND LIMESTONE CEMENT CONFORMING TO ASTM C595/C595M-21 TYPE IL, [8.8] SCG Bangkok Thailand

Physical properties	Unit	Specification	Test Results	Test Method
Air content of mortar	%	12 Max	8.4	ASTM C 185
Autoclave expansion	%	0.80 Max	0.03	ASTM C151/C151M
Blaine	cm2/g	A	4210	ASTM C 204
Mass density	g/cm3	A	3.14	ASTM C 188
Heat of Hydration	J/g(cal/g)	**	301	ASTM C1702
Mortar Bar Expansion *	%	< 0.020	0.004	ASTM C1038
Sulfate Resistance	%	0.10 Max ***	0.07	ASTM C1012
Compressive Strength				
3 days	PSI/MPa	1890 (13.0)	5290 (36.1)	ASTM C 109/C109M
7 days		2900 (20.0)	5900 (40.7)	
28 days		3620 (25.0)	7350 (50.6)	
Time of setting (Vicat)				
Initial set	Minutes	45 Min	110	ASTM C 191
Final set		420 Max	190	
Retained content on				
.+Sieve 45µm	%	10.0 Max	0.95	ASTM C 430
Chemical properties				
MgO	%	A	1.3	ASTM C114
SO3	%	3.0 Max*	2.9	
Loss on ignition (LOI)	%	10 Max	5.2	
Insoluble Residue	%	A	Mill Cert-	
Limestone in cement	%	5.0-15.0	8.81	
CaCO2 in Limestone	%	70 or >	96.36	
SiO2	%	A	19.7	
AI203	%	A	4.1	
Fe203	%	A	2.9	
CaO	%	A	67.6	
K2O	%	A	0.40	
Na2O	%	A	0.14	
R2O (Total alkalies)	%	A	0.39	
Chloride content	%	A	0.02	

Remark:

This cement meets ASTM C595 and AASHTO M240 Specification for Type IL Portland Limestone Cement.

A = Not applicable.
** = Default table maximum may be exceeded if C1038/C1038M limit is met.*
*** = Meets 3d Moderate Heat – MH*
****=Meets 180d Moderate Sulfate – MS*

October 22, 2026

Daniel K. Paaaina III
Chemist